

SUNWORKER TOP

Technical sheet

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Composition	PES high - tenacity(42%) coating PVC(42%) et PU (16%)		
Backing / Finish	Double-sided PVC-PU coating - Lowick system		
Weave	Rachel Trameur - superior tear resistance		ISO 7211-1
Weight	360	g/m ²	ISO 3801
Thickness	0.42	mm	ISO 5084
Angular deviation	<2		
Width	300	cm	EN 1773

FABRIC RESISTANCE

Tensile strength	220	150	daN/5cm	ISO 13934-1
Elongation at break	30	30	%	ISO 13934-1
Tear strength	10	10	daN	ISO 13937-1
Stiffness	1100-1400	350-500	mN	ISO 2493
Elongation under load	1,5	4,2	%	MO LAB 025
Schmerber	>10000		mm	ISO 811

This product's values may vary with a tolerance of \pm 5%

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK

