

SUNBRELLA SOURCE

Karta techniczna



CHARAKTERYSTYKA	WARTOŚCI		JEDNOSTK I	STANDARDY
	OSNOWA	WĄTEK		

OGÓLNA CHARAKTERYSTYKA

Skład	100% akrylowy roztwór barwiony Sunbrella			
Wykończenie	Resin based anti-fongi coating, water and UV resistant			
Splot	Canvas			ISO 7211-1
Gramatura	356		g/m ²	ISO 3801
Szerokosc rolki	152		cm	EN 1773
Długosc rolki	50		ml	



ODPORNOŚC TKANINY

Wytrzymałosc na rozciąganie	125	115	daN/5cm	ISO 13934-1
Odpornosc na rozdarcie	2.5	2.3	daN	ISO 13937-1
Schmerber	900		mm	ISO 811
Test natrysku	5		Class / 5	ISO 4920
Odpornosc na olej	4		Class / 8	ISO 14419

ODPORNOŚC KOLORÓW

Odpornosc kolorów na UV - na zewnątrz - 1000h	4-5		Class / 5	ISO 105 B04
Odpornosc kolorów na UV - wewnątrz	7-8		Class / 8	ISO 105 B02
Odpornosc kolorów na tarcie na sucho	5		Class / 5	ISO 105X12
Odpornosc kolorów na tarcie na mokro	5		Class / 5	ISO 105X12

UZYTKOWANIE

Gwarancja	5	Lat	
Zalecane uzytkowanie	Sprayhood, Rear enclosure, Bimini , Cockpit enclosure, Windscreen cover, Dodger, Console cover, Winter cover, Seat cover		

This product's values may vary with a tolerance of ± 5%

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK