

OPERA

Technical sheet

| CHARACTERISTICS | VALUES | | UNITS | STANDARDS |
|-----------------|--------|------|-------|-----------|
| | WARP | WEFT | | |

GENERAL CHARACTERISTICS

| | | | | |
|------------------|--|--|------|------------|
| Composition | 100% solution dyed acrylic Sunacryl | | | |
| Backing / Finish | Cleangard special dirt-resistance and awning water resistant treatment | | | |
| Weave | Jacquard | | | ISO 7211-1 |
| Weight | 330.00 | | GMET | ISO 3801 |
| Thickness | 0.70 | | MM | ISO 5084 |
| Width | 120 | | CM | EN 1773 |
| Roll length | 60 | | ML | |

FABRIC RESISTANCE

| | | | | |
|-----------------------|--------|-------|------|-------------|
| Tensile strength | 180.00 | 90.00 | DAN5 | ISO 13934-1 |
| Elongation at break | 25 | 26 | % | ISO 13934-1 |
| Tear strength | 5.30 | 3.00 | DAN | ISO 13937-1 |
| Stiffness | 3000 | 1300 | MN | ISO 2493 |
| Schmerber | 200 | | MM | ISO 811 |
| Spray test | 5 | | CLA5 | ISO 4920 |
| Resistance durability | 4 | | CLA4 | EN 13561 |

COLOUR-FASTNESS

| | | | | |
|--------------------------------------|-----|--|------|-------------|
| Colour fastness UV - outdoor - 1000h | 4-5 | | CLA5 | ISO 105 B04 |
| Colour fastness UV - indoor | 7-8 | | CLA8 | ISO 105 B02 |
| Colour fastness under dry friction | 5 | | CLA5 | ISO 105X12 |
| Colour fastness under wet friction | 5 | | CLA5 | ISO 105X12 |

USES

| | | | | |
|------------------|--|--|----|--|
| Guarantee | 10 | | YE | |
| Recommended Uses | Drop arm awning, Folding arm awning, Exterior velum, Pergola, Sail shade | | | |

This product's values may vary with a tolerance of \pm 5%

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK



Tested for harmful substances
www.oeko-tex.com/standard100

