

SUNBRELLA REEF

Technical sheet



| CHARACTERISTICS | VALUES | | UNITS | STANDARDS |
|-----------------|--------|------|-------|-----------|
| | WARP | WEFT | | |

GENERAL CHARACTERISTICS

| | | | | |
|------------------|-------------------------------|--|------|------------|
| Composition | 100% Sunbrella acrylic | | | |
| Backing / Finish | Water-repellent & Stain-proof | | | |
| Weave | Jacquard | | | ISO 7211-1 |
| Weight | 393.00 | | GMET | ISO 3801 |
| Width | 140 | | CM | EN 1773 |
| Roll length | 45 | | ML | |

FABRIC RESISTANCE

| | | | | |
|--------------------------------|--------|---------|------|-------------|
| Tensile strength | 108.00 | 201.00 | DAN5 | ISO 13934-1 |
| Elongation at break | 21 | 30 | % | ISO 13934-1 |
| Schmerber | 94 | | MM | ISO 811 |
| Spray test | 5 | | CLA5 | ISO 4920 |
| Seam slippage (180 N) | < 8 | < 4 | MM | ISO 13936-2 |
| Stitching strength | 478 | 493 | DAN | ISO 13935-2 |
| Stability on 30 deg. C washing | +/- 2 | +/- 1.6 | % | ISO 5077 |

COLOUR-FASTNESS

| | | | | |
|--------------------------------------|-----|--|------|-------------|
| Colour fastness UV - outdoor - 1000h | 4-5 | | CLA5 | ISO 105 B04 |
| Colour fastness UV - indoor | 7-8 | | CLA8 | ISO 105 B02 |
| Colour fastness under dry friction | 5 | | CLA5 | ISO 105X12 |
| Colour fastness under wet friction | 5 | | CLA5 | ISO 105X12 |
| Colour fastness 40°C washing | 5 | | CLA5 | ISO 105 C06 |

USES

| | | | |
|------------------|-----------------------------|----|--|
| Guarantee | 5 | YE | |
| Recommended Uses | Cushions, Seating, Planking | | |

CARE



This product's values may vary with a tolerance of $\pm 5\%$

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK

