

# SWK ZIP (SUNWORKER ZIP)

## Technical sheet

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		



### GENERAL CHARACTERISTICS

Composition	high-tenacity polyester/PVC 50/50		
Backing / Finish	Double-sided PVC coating - Lowick system		
Weave	Rachel Trameur- superior tear resistance		ISO 7211-1
Weight	400.00	g/m <sup>2</sup>	ISO 3801
Openess factor	4	%	
Width	320	cm	EN 1773
Roll length	34	ml	

### FABRIC RESISTANCE

Tensile strength	280.00	340.00	daN/5cm	ISO 13934-1
Elongation at break	25	26	%	ISO 13934-1
Tear strength	14.00	14.00	daN	ISO 13937-1
Stiffness	1600	1100	mN	ISO 2493
Fire resistance / Euroclasse	Euroclass B-s2 d0			EN 13501-1
Fire resistance / FR	M1			NF P 92 503
Fire resistance / DE	B1 (DIN 4102)			DIN 4102
Fire resistance / IT	C1 (UNI 9177)			UNI 9176
Fire resistance / ES	Clase 1			UNE-EN 13773

### COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4 or 4.5	Class / 5	ISO 105 B04
Colour fastness UV - indoor	7	Class / 8	ISO 105 B02
Colour durability	4 or 3	Class / 4	EN 13561

### USES

Temperature of use	-30>>+70		
Guarantee	5	years	
Recommanded Uses	Vertical screen, pergola screen, veranda screen		

*This product's values may vary with a tolerance of ± 5%*

**Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration**

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - [www.dickson-constant.com/en/UK](http://www.dickson-constant.com/en/UK)

