

# SWK15 (SUNWORKER OPEN)

## Technical sheet



CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

### GENERAL CHARACTERISTICS

Composition	high-tenacity polyester/PVC 50/50		
Backing / Finish	Double-sided PVC coating - Lowick system		
Weave	Rachel Trameur - superior tear resistance		ISO 7211-1
Weight	360	g/m <sup>2</sup>	ISO 3801
Thickness	0.55	mm	ISO 5084
Openess factor	15	%	
Angular deviation	< 2		
Width	305	cm	EN 1773
Roll length	30	ml	

### FABRIC RESISTANCE

Tensile strength	260	180	daN/5cm	ISO 13934-1
Elongation at break	23	23	%	ISO 13934-1
Tear strength	40	30	daN	DIN 53.363
Stiffness	1600	700	mN	ISO 2493
Elongation under load	1.3	2.5	%	MO LAB 025
Resistance durability	4		Class / 4	EN 13561
Fire resistance / FR	M2			NF P 92 503
Fire resistance / DE	B1			DIN 4102

### COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4-5		Class / 5	ISO 105 B04
Colour durability	4 * * M005-M006-M654 : class 3/4		Class / 4	EN 13561

### USES

Temperature of use	-30 >> +70		
Guarantee	5	years	
Recommended Uses	Exterior velum, Pergola, Conservatory blind, Vertical blind, Sail shade, Roll up valance, Vertical blinds, Screen pergola		

*This product's values may vary with a tolerance of ± 5%*

**Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration**

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - [www.dickson-constant.com/en/UK](http://www.dickson-constant.com/en/UK)

